

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A pressure sensitive adhesive product obtained by curing a pressure sensitive adhesive composition

which comprises the following components (A), (B) and (C):

(A) a hydrolyzable silyl group-containing organic polymer containing at least 1.3 hydrolyzable silyl groups per molecule and having a number average molecular weight of 15,000 to 100,000, the main chain of the organic polymer being substantially composed of a repeating unit or units represented by the general formula -R¹-O- (R¹ being a divalent alkylene group);

(B) a hydrolyzable silyl group-containing organic polymer containing 0.3 to 1.3 hydrolyzable silyl groups per molecule and having a number average molecular weight of 500 to 15,000, the main chain of which polymer being substantially composed of a repeating unit or units represented by the general formula -R¹-O- (R¹ being a divalent alkylene group);

(C) a tackifier resin selected from the group consisting of terpene resins, terpene phenol resins, petroleum resins, rosin ester resins, and admixtures thereof, and

a compounding ratio of which is 5 to 150 parts by weight, relative to a combined total of 100 parts by weight of (A) and (B).

2. (canceled).

3. (previously presented): The pressure sensitive adhesive product according to Claim 1 wherein the main chain of the hydrolyzable silyl group-containing organic polymers (A) and (B) is substantially polyoxypropylene.

4. (currently amended): The pressure sensitive adhesive product according to Claim 1 wherein the hydrolyzable silyl group of the hydrolyzable silyl group-containing organic polymers (A) and (B) is represented by the following general formula (I):



(wherein, R^2 represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3).

5. (currently amended): The pressure sensitive adhesive product according to Claim ~~2~~1 wherein the main chain of the hydrolyzable silyl group-containing organic polymers (A) and (B) is substantially polyoxypropylene.

6. (currently amended): The pressure sensitive adhesive product according to Claim ~~2~~1 wherein the hydrolyzable silyl group of the hydrolyzable silyl group-containing organic polymers (A) and (B) is represented by the following general formula (I):



(wherein, R^2 represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3).

7. (currently amended): The pressure sensitive adhesive product according to Claim 3 wherein the hydrolyzable silyl group of the hydrolyzable silyl group-containing organic polymers (A) and (B) is represented by the following general formula (I):



(wherein, R^2 represents a substituted or unsubstituted monovalent organic group containing 1 to 20 carbon atoms, X represents a hydrolyzable group, and a represents 1, 2 or 3-).